

Rec'd PCT/PTO 15 APR 2005

531353

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
22 July 2004 (22.07.2004)

PCT

(10) International Publication Number
WO 2004/061018 A1

(51) International Patent Classification⁷: C09D 4/00, 5/00

Circle, Berwyn, PA 19312 (US). TRONCO, Henry, A., Jr.
[US/US]; 756 Rhoads Drive, Springfield, PA 19064 (US).

(21) International Application Number:
PCT/US2003/041625

(74) Agent: DESMUKH, Sudhir, G.; E.I. DUPONT DE
NEMOURS AND COMPANY, LEGAL PATENT
RECORDS CENTER, 4417 Lancaster Pike, Wilmington,
DE 19805 (US).

(22) International Filing Date:
30 December 2003 (30.12.2003)

(25) Filing Language:

English

(81) Designated States (*national*): CA, MX, US.

(26) Publication Language:

English

(84) Designated States (*regional*): European patent (AT, BE,
BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU,
IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR).

(30) Priority Data:
60/433,129 31 December 2002 (31.12.2002) US

Published:

- with international search report
- before the expiration of the time limit for amending the
claims and to be republished in the event of receipt of
amendments

(71) Applicant (*for all designated States except US*): E.I. DU
PONT DE NEMOURS AND COMPANY [US/US]; 1007
Market Street, Wilmington, DE 19898 (US).

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): MA, Sheau-Hwa
[US/US]; 1235 Twaddell Drive, West Chester, PA 19382
(US). MATTHEWS, James, F. [US/US]; 11 Lakeview

*For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.*

(54) Title: PROCESS FOR PRODUCING MULTI-COAT SYSTEM ON SUBSTRATE

(57) **Abstract:** The present invention relates to a process for producing a multi-coat system on various substrates, particularly au-
tomotive bodies. A crosslinkable component of the composition includes an acid functional acrylic copolymer polymerized from a
monomer mixture comprising 2 percent to 12 percent of one or more carboxylic acid group containing monomers, percentages based
on total weight of the acid functional acrylic copolymer, and 0.2 percent to 2 percent of amorphous silica, percentages based on total
weight of the crosslinkable component. The crosslinking component can includes polyisocyanates, melamines, or a combination
thereof.

WO 2004/061018 A1